

Technical Data Sheet

DOWSIL[™] 795 Silicone Building Sealant

Neutral, one part silicone sealant

Features & Benefits	Suitable for most new construction and remedial sealing applications Versatile – high performance structural glazing and weather sealing from a single product Available in 15 standard colors; custom colors also available Excellent weatherability virtually unaffected by sunlight, rain, snow, ozone and temperature extremes of -40°F (-40°C) to 300°F (149°C) Excellent unprimed adhesion to a wide variety of construction materials and building components, including anodized, alodined, most coated and many Kynar [®] painted aluminums Ease of application – ready to use as supplied Ease of use – all temperature gunnability, easy tooling and low-odor cure byproduct Meets global standards (Americas, Asia and Europe)
Composition •	One part, neutral cure, RTV silicone sealant
Applications • •	Structural and nonstructural glazing Structural attachment of many panel systems Panel stiffener applications Weather sealing of most common construction materials including glass, aluminum, steel, painted metal, EIFS, granite and other stone, concrete, brick and plastics

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result
	As Supplied		
ASTM C 679	Tack Free Time, 50% RH	hours	3
	Curing Time at 25°C (77°F) and 50% RH	days	7–14
	Full Adhesion	days	14–21
ASTM C 639	Flow, Sag or Slump	inches (mm)	0.1 (2.54)
	Working Time	minutes	20-30
	VOC Content ²	g/L	32

1.

ASTM: American Society for Testing and Materials Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and 2. exclusive of water and exempt compounds.

Typical Properties (Cont.)

Test	Property	Unit	Result
	As Cured After 21 days at 25°C (77°F) and 50% RH		
ASTM D 2240	Durometer Hardness, Shore A	points	35
ASTM C 794	Peel Strength	lb/in (kg/cm)	32 (5.7)
ASTM C 1135	Tension Adhesion Strength		
	At 25% extension	psi (MPa)	45 (0.310)
	At 50% extension	psi (MPa)	60 (0.414)
ASTM C 719	Joint Movement Capability	percent	± 50
ASTM C 1248	Staining (granite, marble, limestone, brick and concrete)		None
	As Cured After 21 days at 25°C (77°F) and 50% RH Followed by 10,000 Hours in a QUV Weatherometer, ASTM G 53		
ASTM C 1135	Tensile Adhesion Strength		
	At 25% extension	psi (MPa)	35 (0.241)
	At 50% extension	psi (MPa)	50 (0.345)
Approvals/	U	he requirements of:	
Approvals/ Specificatior	 DOWSIL 795 Silicone Building Sealant meets the requirements of: Federal Specification TT-S 001 543A (COM-NBS) Class A for silicone building sealants Federal Specification TT-S-00230C (COM-NBS) Class A for one component building sealants ASTM Specification C 920 Type S, Grade NS, Class 50, Use NT, G, A and O ASTM Specification C 1184 for structural silicone sealants Canadian Specification CAN2-19.13- M82 		
	SEALANT • WATERPROOFING RESTORATION INSTITUTE Issued to: Dow Silicones Corporation Product: Dowsil" 795 Silicone Building Sealant C719: Pass _ Ext:+50% Comp:-50% Substrate: Glass, Aluminum, Kynar [Glass and Aluminum Substrates were tested unprimed; Dow Corning 1200 OS Primer used on Kynar substrates]		

Colors	DOWSIL 795 Silicone Building Sealant is available in 16 colors: white, limestone, champagne, natural stone, gray, black, bronze, sandstone, adobe tan, dusty rose, rustic brick, blue spruce, anodized aluminum, and charcoal. Custom colors may be ordered to match virtually any substrate.
How To Use	Please consult the <i>Dow Corning Americas Technical Manual</i> , Form No. 62-1112, for detailed information on state-of-the-art application methods and joint design. Preparation Clean all joints, removing all foreign matter and contaminants such as grease, oil, dust,
	water, frost, surface dirt, old sealants or glazing compounds and protective coatings. Application Method Install backing material or joint filler, setting blocks, spacer shims and tapes. Mask areas adjacent to joints to ensure neat sealant lines. Primer is generally not required on non- porous surfaces, but may be necessary for optimal sealing of certain porous surfaces. A test placement is always recommended. Apply DOWSIL 795 Silicone Building Sealant in a continuous operation using positive pressure. (The sealant can be applied using many types of air-operated guns and most types of bulk dispensing equipment.) Before a skin forms (typically within 15 minutes), tool the sealant with light pressure to spread the sealant against the backing material and joint surfaces. Remove masking tape as soon as the bead is tooled.
Handling Precautions	PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.
Usable Life And Storage	When stored at or below 27°C (80°F), DOWSIL 795 Silicone Building Sealant has a shelf life of 12 months from the date of manufacture. Refer to product packaging for "Use By Date."
Packaging Information	DOWSIL 795 Silicone Building Sealant is supplied in 10.3 fl oz. (305 mL) disposable plastic cartridges that fit ordinary caulking guns, 20 fl oz. (590 mL) sausages and 2 and 4.5 gal (7.5 and 17 L) bulk containers.
Limitations	 DOWSIL 795 Silicone Building Sealant should not be used: In structural applications without prior review and approval by your local sales application engineer In below grade applications When surface temperatures exceed 50°C (122°F) during installation On surfaces that are continuously immersed in water On building materials that bleed oils, plasticizers or solvents that may affect adhesion On frost laden or wet surfaces In totally confined joints (the sealant requires atmospheric moisture for cure) If the sealant is intended to be painted (paints do not typically adhere to most silicone sealants) To surfaces in direct contact with food or other food-grade applications

Limitations (Cont.)	This product is neither tested nor represented as suitable for medical or pharmaceutical uses.
Health And Environmental Information	To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.
	For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

Kynar is a registered trademark of Atofina Chemicals Inc.

http://www.consumer.dow.com

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

